

Spring Wire

Diameter/mm	TOLERANCE/m m	Tensile Strength For Wire Grades (N/mm ²)		
		A	B	C
1.00-1.50	±0.015	1850-2220	-----	2090-2450
1.50-2.00	±0.020	1770-2080	-----	1980-2310
2.00-2.50	±0.035	1670-1820	1750-1900	1970-2140
2.50-2.70		1640-1790	1720-1870	1950-2120
2.70-3.00		1620-1770	1700-1850	1930-2100
3.00-3.20		1600-1750	1680-1830	1910-2080
3.20-3.50	±0.045	1580-1730	1660-1810	1900-2060
3.50-4.00		1550-1700	1620-1770	1870-2030
4.00-4.20		1540-1690	1610-1760	1860-2020
4.20-4.50		1520-1670	1590-1740	1850-2000
4.50-4.70		1510-1660	1580-1730	1840-1990
4.70-5.00		1500-1650	1560-1710	1830-1980
5.00-5.60		1470-1620	1540-1690	1800-1950
5.60-6.00	±0.050	1460-1610	1520-1670	1780-1930
6.00-6.50		1440-1590	1510-1660	1760-1910
6.50-7.00		1430-1580	1500-1650	1740-1890
7.00-8.00		1400-1550	1480-1630	1710-1860
8.00-8.50		1380-1530	1470-1620	1700-1850

Product link : <https://www.fivestar-wire.com/?p=1227>